



**Laboratory Testing Report**

<i>Company</i>	Noroo Paint And Coatings
<i>Contact Name</i>	Sung Woo Jung swjung@noroo.com Yun-jae So syj@noroo.com
<i>Report Date</i>	February 25, 2019
<i>Category</i>	Detailed Performance
<i>Category Type</i>	Initial
<i>IPS#</i>	3025-I-2019-4-17000
<i>MPI Category #</i>	4
<i>Product Label</i>	Noroo Paint
<i>Product Name</i>	Natural Block Filer
<i>Product Code</i>	NA
<i>Batch Number</i>	119 JAN 1111a
<i>Testing Results</i>	<b>PASS</b>
<i>Approval Expiry Date</i>	Approximately 2 years
<i>Failure Notice</i>	
<i>Comments</i>	
<i>MPI Technical Director</i>	<b>Bob Welch</b>
<i>MPI Senior Admin Assistant</i>	<b>Matt Jacobs</b>
<i>MPI Invoice #</i>	<b>D19-0185</b>

**A pass report is not the final approval.**

**Final approval occurs when the product is published in the MPI Approved Products List.  
The MPI Approved Products List is updated by the 5th of each month.**

**2800 Ingleton Avenue, Burnaby, BC V5C 6G7 Canada  
Tel: 604-298-7578 Fax: 604-298-7571  
Toll-Free Tel: 1-888-674-8937, Toll Free Fax: 888-211-8708  
February 25, 2019**

**■GENERAL INFORMATION**

This paint is based on Acrylic polymer and Pigmented, latex-based block filler intended for use on new interior/exterior new concrete masonry units, for the purpose of filling the surface for subsequent applications of paint.  
 This paint is not intended for use on wood.

**■SUITABLE USE**

Various kinds of ceilings and walls (concrete, P.C., mortar, plaster.)

**■SPECIFICATION**

A. Type: Acrylic Polymer/Block filler/Interior and exterior

B. Drying Times:	5 °C	20 °C	30 °C
Set to Touch	1H	1/2H	1/3H
Dry Hard	2H	1H	2/3H
For Over coat (Min.)	6H	3H	2H

\* H: Hour

C. Consistency: Ready for use

D. Thinner: Tap-Water (Max. 5% at 1st coating,  
 Max. 5% at 2nd coating)

E. Specific Gravity: Appr. 1.68

F. Theoretical Coverage: 10~14 m<sup>2</sup>/L/1 coats/40μ  
 (Dry film thickness)

G. Shade: White and tints

H. Texture: Flat

**■DIRECTION FOR USE**

**A. Surface Preparation**

1. Eliminate oil, water, grit, dirt, marked paint and any foreign matters.

**B. Preparation of Paint**

1. Stir to be mixed uniformly.  
 2. Avoid excessive thinning.

**C. Application**

1. Can be applied by brush, spray.

**■OTHER CAUTIONS -**

- Will not form a homogeneous film below 5 °C (41 °F) or at humidities greater than 95% R.H.
- Don't store or ship the paint at temperatures less than 5 °C (41 °F) nor above 35 °C (95 °F)

3. Surface to be painted shall be prepared an instrument-measured moisture content not exceeding 8% and less than 9 pH.

\* The information and data given herein are based upon tests and experiences considered reliable, and are believed to be accurate. The coverage depends on the shape of surface to be coated, surface roughness, weather conditions during application and application method, so that you are urged fully to review them prior to your practical application.

\* The date of issue: 2008.12

# MATERIAL SAFETY DATA SHEET

## SECTION I GENERAL INFORMATION

- A. PRODUCT NAME: Natural Block Filler ( MPI 4 )  
Block Filler, Latex, Interior/Exterior
- B. MANUFACTURERS NAME: NOROO Paint & Coatings Co., Ltd.  
615 PARK DAL DONG, AN YANG CITY  
KYUNG KI DO, KOREA  
TEL: (031)467-6150

## SECTION II COMPOSITION

CHEMICAL NAME	CAS NO	CONTENTS
ACRYLIC POLYMER	NOT HAZARD	10~20
ETHYLENE GLYCOL	107-21-1	1 MAX
WATER	7732-18-5	20~30
CALCIUM CABONATE	13463-67-7	50~70
S1	-	0~3

## SECTION III PHYSICAL PROPERTIES

BOILING RANGE	200~225 deg.F
EVAPORATION RATE	SLOWER THAN ETHER
VAPOR DENSITY	HEAVIER THAN AIR
% VOLATILE VOLUME	50 MAX
SPECIFIC GRAVITY	1.6~1.7
VISCOSITY	100~120KU

## SECTION IV - FIRE AND EXPLOSION HAZARD DATA

FLAMMABILITY CLASSIFICATION:

FLASH POINT: NOT ESTABLISHED

LEL: N/A

EXTINGUISHING MEDIA: FOAM, ALCOHOL FOAM, CO2, DRY CHEMICAL, WATER FOG

UNUSUAL FIRE AND EXPLOSION HAZARDS:

EXTINGUISHING MEDIA ABOVE IS RECOMMENDED ON DRIED FILMS OF THIS MATERIAL THAT IS BURNING. THIS MATERIAL IS NON-COMBUSTIBLE BUT DRIED FILMS ARE CAPABLE OF BURNING AND SUPPORTING COMBUSTION WHEN IN CONTACT WITH OPEN FLAMES.

SPECIAL FIREFIGHTING PROCEDURES:

OBSERVE RECOMMENDED PROCEDURES IN HANDLING FIRE AREAS. WEAR APPROPRIATE FIRE FIGHTING EQUIPMENT INCLUDING A SELF CONTAINED BAEATHING APPARATUS.

## SECTION V - HEALTH HAZARD DATA

EFFECTS OF OVEREXPOSURE:

VAPOR ODORS MAY CAUSE IRRITATION IN THE UPPER AND LOWER RESPIRATORY TRACTS, NAUSEA, HEADACHES, AND DIZZINESS. EYE CONTACT CAN CAUSE IRRITATION, REDNESS, AND VOMITING, DIARRHEA, AND GASTROINTESTINAL IRRITATION.

MEDICAL CONDITIONS PRONE TO AGGRAVATION BY EXPOSURE:

OVEREXPOSURE TO VAPORS CAN PRODUCE HEADACHES, DIZZINESS, AND NAUSEA.

PRIMARY ROUTE(S) OF ENTRY: INHALATION, INGESTION

EMERGENCY AND FIRST AID PROCEDURES:

IF AFFECTED BY VAPORS, MOVE PERSON TO FRESH AIR. APPLY ARTIFICIAL RESPIRATION TO PERSON WHO LOSES CONSCIOUSNESS AND CALL A DOCTOR IMMEDIATELY. TREAT EYE AND SKIN CONTACT BY THOROUGHLY WASHING WITH CLEAN WATER. IF IRRITATION PERSISTS SEE A DOCTOR IMMEDIATELY. IF MATERIAL IS INGESTED AND THE PERSON IS CONSCIOUS GIVE TWO GLASSES OF WATER TO DRINK AND CALL A DOCTOR IMMEDIATELY.

## SECTION VI – REACTIVITY DATA

STABILITY: STABLE

HAZARDOUS POLYMERIZATION: WILL NOT OCCUR

HAZARDOUS POLYMERIZATION INFORMATION IS NOT ESTABLISHED.

HAZARDOUS DECOMPOSITION PRODUCTS:

BURNING CAN PRODUCE CARBON DIOXIDE AND OR CARBON MONOXIDE.

CONDITIONS TO AVOID:

AVOID TEMPERATURES BELOW 40 degrees Farenheit. AVOID FREEZING CONDITIONS.

INCOMPATIBILITY (MATERIALS TO AVOID):

AVOID MATERIALS THAT REACT WITH WATER, ALSO STRONG ACIDS AND ALKALAI S.

## SECTION VII – SPILL OR LEAK PROCEDURES

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED:

DIKE AND ABSORB SPILLED MATERIAL WITH INERT ABSORBENT MATERIAL SUCH AS SAND, EARTH, AND SAW DUST. USE RAGS TO CLEAN UP SALL AMOUNTS OF SPILLED MATERIAL.

WASTE DISOSAL METHOD:

COLLECT MATERIAL CONTAMINATED ABSORBENT AND RAGS INTO A DISPOSABLE CONTAINER AND DISPOSE OF IN ACCORDANCE TO LOCAL, STATE, AND FEDERAL REGULATIONS. CONSULT WITH YOUR LOCAL HAZARDOUS WASTE REGULATIORS REGARDING LANDFILL DUMPING.

## SECTION VIII – SAFE HANDLING AND USE INFORMATION

RESPIRATORY PROTECTION:

WEAR APPROVED ORGANIC VAPOR RESPIRATOR UNLESS VENTILATION EQUIPMENT IS ADEQUATE TO KEEP AIRBORNE CONCENTRATIONS BELOW THE EXPOSURE STANDARDS.

VENTILATION:

GENERAL MECHANICAL VENTILATION MAY BE SUFFICIENT TO KEEP PRODUCT VAPOR CONCENTRATIONS BELOW SPECIFIED TLV RANGES. IF INADEQUATE, USE LOCAL EXHAUST.

PROTECTIVE GLOVES:

USE IMPERMEABLE SOLVENT RESISTANT GLOVES TO PROTECT FROM SKIN CONTACT.

EYE PROTECTION:

USE SAFETY GOGGLES, CHEMICAL SAFETY GLASSES AND OR FACE SHIELDS TO PROTECT EYES

OTHER PROTECTIVE EQUIPMENT:

IMPERMEABLE APRONS AND PROTECTIVE CLOTHING ARE ADVISED WHEN WORKING WITH THIS PRODUCT. THE USE OF HEAD CAPS ARE RECOMMENDED WHENEVER POSSIBLE.

HYGIENIC PRACTICES:

EYE WASHES AND SAFETY SHOWERS IN THE WORKPLACE ARE RECOMMENDED.

## SECTION IX – SPECIAL PRECAUTIONS

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING:

KEEP CONTAINERS CLOSED WHEN NOT IN USE. DO NOT STORE OR HANDLE NEAR HEAT, FLAMES AND STRONG OXIDANTS. INSPECT FOR LEAKS IN ALL CONTAINERS.

OTHER PRECAUTIONS:

DO NOT STORE IN FREEZING AREAS. KEEP ABOVE 40 degrees F. KEEP OUT OF REACH OF CHILDREN.

\* \* DISCLAIMER- THE INFORMATION CONTAINED HEREIN IS BASED ON DATA CONSIDERED  
\* \* ACCURATE. HOWEVER, NO WARRANTY, WHETHER EXPRESSED OR IMPLIED IS MAE.

# TEST REPORT

1. No : SSR2802016

2. Client

- o Name : NOROO Paint &Coatings Co., Ltd. Kim Soo Kyoung
- o Address : 615, Bakdal 2-dong, Manan-gu, Anyang-si, Gyeonggi-do, Korea
- o Date of Receipt : 2012/08/02
- o Date of Issued : 2013/02/19

3. Use of Report : Quality management

4. Test Sample : Natural Block Filer(MPI #4)

5. Test Results

Test Items	Unit	Sample	Test Results	Test method used
Consistency	K.U.	1	123	MPI # 4 : 2010
Dry time, Dry hard	min	1	30	MPI # 4 : 2010
Finess of Grind	NS	1	3	MPI # 4 : 2010
Total Volume Solid	%	1	54	MPI # 4 : 2010
Alkali Resistance	-	1	pass	MPI # 4 : 2010
Topcoat Adhesion	-	1	5B	MPI # 4 : 2010
Filling and Sealing Properties	-	1	No pinhole	MPI # 4 : 2010
Early Water Resistance	-	1	pass	MPI # 4 : 2010
VOCs content	g/L	1	6.9	USEPA Method 24 : 2000

- - - - End of Report - - - -

Affirmation	Tested by	Technical Manager
	Name : <i>Yoo Chang Soo</i>	Name : Kim, Sang Chul <i>Kim Sang Chul</i>
Our report apply only to the standard or procedures identife and to the sample(s) tested unless otherwise specified. The test results are not indicative of repressentative of the qualities of the lot from which the sample was taken or of apparently identical or similar products.		

**Korea Conformity Laboratories** President Jae Bi *Jae Bin Song*

Address : 459-28, Gasan-dong, Geumcheon-Gu, Seoul, Korea 031-888-9463

Result Inquiry : Advanced Materials Reliability Center ☎031-429-3454